

Amendments To The Specification:

In the English translation of sheet 1, please amend the title at lines 1 and 2, as follows:

~~Apparatus~~ Device and ~~process~~ method for removing surface ~~regions~~ areas of a component

In the English translation document, please add the paragraph at page 1 line 3, after the title, as follows:

--CROSS REFERENCE TO RELATED APPLICATION

This application is the US National Stage of International Application No. PCT/DE03/00953, filed March 21, 2003 and claims the benefit thereof. The International Application claims the benefits of German application No. 10215374.4 DE filed April 8, 2002, and German application No. 10259365.5 DE filed December 18, 2002, all of the applications are incorporated by reference herein in their entirety.--

In the English translation document, please add the section heading at page 1 line 3, after the newly added CROSS REFERENCE TO RELATED APPLICATION section, as follows:

--FIELD OF THE INVENTION--

In the English translation document, please amend paragraph at page 1 line 4 as follows:

The invention relates to an apparatus and a process for removing surface regions of a component as described in the claims 1 or 2, respectively.

In the English translation document, please add the section heading at page 1 line 7, as follows:

--BACKGROUND OF THE INVENTION--

In the English translation document, please add the section heading at page 1 line 22, as follows:

--SUMMARY OF THE INVENTION--

In the English translation document, please amend paragraph at page 1 line 27 as follows:

The object is achieved by an apparatus and a process for the removal of surface regions from a component as described in the claims 1 and 2, respectively.

In the English translation document, please add the section heading at page 1 line 33, as follows:

**--BRIEF DESCRIPTION OF THE DRAWINGS--**

In the English translation document, please add the section heading at page 2 line 7, as follows:

**--DETAILED DESCRIPTION OF THE INVENTION--**

## DEVICE AND METHOD FOR REMOVING SURFACE AREAS OF A COMPONENT

### CROSS REFERENCE TO RELATED APPLICATION

[0001] This application is the US National Stage of International Application No. PCT/DE03/00953, filed March 21, 2003 and claims the benefit thereof. The International Application claims the benefits of German application No. 10215374.4 DE filed April 8, 2002, and German application No. 10259365.5 DE filed December 18, 2002, all of the applications are incorporated by reference herein in their entirety.

### FIELD OF THE INVENTION

[0002] The invention relates to an apparatus and a process for removing surface regions of a component as described in the claims.

### BACKGROUND OF THE INVENTION

[0003] Hitherto, components which have been coated with coatings of type MCrAlY or ZrO<sub>2</sub> have had the coating removed, for example, by acid stripping in combination with sand blasting or by high-pressure water blasting.

[0004] EP 1 122 323 A1 and US 5,944,909 show examples of the chemical removal of surface regions.

[0005] EP 1 941 34 A1, EP 1 010 782 A1 and US-A 6,165,345 disclose methods for the electrochemical removal of metallic coatings (stripping).

[0006] The processes listed above are time-consuming and therefore expensive.

### SUMMARY OF THE INVENTION

[0007] It is an object of the invention to provide an apparatus and a process in which the removal of the coating takes place more quickly and economically.

[0008] The object is achieved by an apparatus and a process for the removal of surface regions from a component as described in the claims.

[0009] Further advantageous configurations and process steps are listed in the corresponding subclaims.

#### BRIEF DESCRIPTION OF THE DRAWINGS

[0010] In the drawing:

[0011] Figure 1 shows an apparatus according to the invention,

[0012] Figure 2 shows a time curve of a current of a current pulse generator, and

[0013] Figure 3 shows a further time curve of a current from a current pulse generator.

#### DETAILED DESCRIPTION OF THE INVENTION

[0014] Figure 1 shows an apparatus 1 according to the invention. The apparatus 1 comprises a vessel 4 in which an electrolyte 7 there is arranged. An electrode 10 and a component 13 are arranged in the electrolyte 7. The electrode 10 and the component 13 are electrically connected to a current/voltage pulse generator 16. The component 13 is, for example, a coated turbine blade or vane, the substrate of which is a nickel- or cobalt- base superalloy, to which a metallic layer has been applied to serve, for example, as a corrosion-resistant or anchoring layer. A layer of this type in particular has the composition MCrAlY, where M stands for an element iron, cobalt or nickel.

[0015] The coating has been corroded during use of the turbine blade or vane 13. The surface region 25 which has been formed as a result (as indicated by dashed lines) is to be removed by the process according to the invention and the apparatus 1 according to the invention. It is also possible for layer regions 25 which have been formed by corrosion, oxidation or other forms of degradation to be removed from a component 13 which does not have a

coating, these layer regions being in the vicinity of the surface.

[0016] The current pulse generator 16 generates a pulsed current/voltage signal (Figure 2).

[0017] An ultrasound probe 19, which is operated by an ultrasound source 22, may optionally be arranged in the electrolyte 7. The ultrasound excitation improves the hydrodynamics of the process and thereby assists the electrochemical reaction.

[0018] Figure 2 shows an example of a current/voltage curve of the current/voltage pulse generator 16.

[0019] The current pulse signal or the voltage pulse is, for example, square-wave (pulse shape) and has a pulse duration  $t_{on}$ . Between the individual pulses there is an interval of length  $t_{off}$ . Furthermore, the current pulse signal is defined by its current level  $I_{max}$ .

[0020] The current ( $I_{max}$ ) which flows between the electrode 10 and the component 13, the pulse duration ( $t_{on}$ ) and the pulse interval ( $t_{off}$ ) have a significant influence on the electrochemical reaction by accelerating the latter.

[0021] Figure 3 shows an example of a series of current pulses 40 which are repeated. A sequence 34 comprises at least two blocks 77. Each block 77 comprises at least one current pulse 40. A current pulse 40 is characterized by its duration  $t_{on}$ , the level  $I_{max}$  and its pulse shape (square-wave, delta, etc.). Other important process parameters are the intervals between the individual current pulses 40 ( $t_{off}$ ) and the intervals between the blocks 77.

[0022] The sequence 34 comprises, for example, a first block 77 of three current pulses 40 between each of which there is an interval. This is followed by a second block 77, which has a higher current level and comprises six current pulses 40. After a further interval, there then follow four current pulses 40 in the opposite direction, i.e. with a reversed polarity.

[0023] The sequence 34 is finished by a further block 77 of four current pulses.

[0024] The sequence 34 can be repeated a number of times.

[0025] The individual pulse times  $t_{on}$  are preferably of the order of magnitude of approximately 1 to 10 milliseconds. The time duration of the block 77 is of the order of magnitude of up to 10 seconds, so that up to 500 pulses are emitted in one block 77.

[0026] The application of a low potential (base current) both during the pulse sequences and during the intervals is optionally possible.

[0027] The parameters of a block 77 are matched to a constituent of an alloy which, by way of example, is to be removed in order to optimize the removal of this constituent. This can be determined in individual tests.

PATENT CLAIMS:

1. – 9. (canceled)

10. (new) An apparatus for removing a corroded region from a turbine component, comprising:

a vessel sized and configured to containing an electrolyte that the component;

an electrode arranged in the electrolyte and electrically connected to the component;

an electrical current pulse generator electrically connected between electrode and component, the electrical current pulse generator generating current pulses; and

an ultrasound probe arranged in the vessel and within the electrolyte.

11. (new) The apparatus as claimed in claim 10, wherein the corroded region is a coated region.

12. (new) The apparatus as claimed in claim 10, wherein a positive or a negative potential is applied to the component to generate a base current or base voltage.

13. (new) A process for removing a coating from a surface region of a component,

arranging the component and an electrode in an electrolyte;

electrically connecting the component, the electrode, and a current generator;

generating a pulsed current or pulsed voltage by the current generator;

forming a sequence of current/voltage pulses by a plurality of different blocks with a block having a current pulse; and

combining a plurality of current/voltage pulses in the sequence the electrolytic coating removal.

14. (new) The process as claimed in claim 13, wherein a positive or a negative potential is applied to the component to generate a base current or base voltage.
15. (new) The process as claimed in claim 13, wherein an ultrasound probe is placed in the electrolyte.
16. (new) The process as claimed in claim 13, wherein a positive and a negative current/voltage pulses are used for the electrolytic coating removal.
17. (new) The process as claimed in claim 13, wherein a block is defined by a plurality of current pulses, pulse duration, pulse interval, current level, and pulse shape.
18. (new) The process as claimed in claim 13, wherein a block is matched to a constituent of an alloy to be removed in order to boost the removal of the constituent of the alloy.
19. (new) The process as claimed in claim 13, wherein the coating removed is an of  $M\text{CrAlY}$ , where M is an element selected from the group consisting of iron, cobalt or nickel.
20. (new) The process as claimed in claim 13, wherein a base current is superimposed on the current pulses and the intervals.
21. (new) The process as claimed in claim 13, wherein a base current is superimposed on the current pulses or the intervals.
22. (new) The process as claimed in claim 13, wherein the current voltage pulse is a square wave shape pulse.
23. (new) The process as claimed in claim 13, wherein the current current pulse is a square wave shape pulse.
24. (new) The process as claimed in claim 13, wherein the pulse times range from 1 to 10 milliseconds.



25. (new) The process as claimed in claim 13, wherein a low base current during the pulse sequences and during the intervals is used.

26. (new) The process as claimed in claim 13, wherein the plurality of current/voltage pulses are combined repeatedly.

ABSTRACT

Apparatus and process for removing surface regions of a component. The prior art involves removing surface regions of a metallic component by means of electrochemical processes. The electrochemical process is accelerated by the use of a current pulse generator.